Report Number : **VNMT16034374**



Hochiminh office: 1st Floor, E.Town EW Building, 364 Cong Hoa Street, Ward 13, Tan Binh District, Ho Chi Minh City, Vietnam.
Tel : (84-8) 62971099 Fax : (84-8) 62971098 Email : consumergoods.vietnam@intertek.com
Hanoi office: 3rd Floor, Au Viet Building, No. 01 Le Duc Tho Street, Mai Dich Ward, Cau Giay District, Hanoi.
Tel : (84-4) 37337094 Fax : (84-4) 37337093 Website : www.intertek.com

TEST REPORT

NUMBER : VNMT16034374
DATE : 16-Aug-2016

APPLICANT : **DOAN KET PRODUCTION IMPORT EXPORT COMPANY LIMITED**
25/54/2B HO VAN LONG STR, TAN TAO WARD,
BINH TAN DIST.,, HOCHIMINH CITY, VIET NAM
ATTN : **MR.HUNG**

Sample Description As Declared	: Poly Taffeta 190T
Color	: Navy 1914
No. of Sample	: 01
Fiber Content	: 100% Polyester
End Uses	: Men's And Women's Wear
Fabric Weight:	: 58 g/m²
Style No.	: DKP-141
Order No./PO No.	: -
Article No.	: -

Applicant Provided Care Instructions :
Machine Wash At 40°C

Date Received/Date Test Started : 11 Aug 2016
Date Confirmation Received : -

TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO ENCLOSED PAGE(S)

AUTHORIZED BY
FOR INTERTEK VIETNAM LTD. [HO CHI MINH]

PHUONG LE
SOFTLINES MANAGER

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)

Intertek Vietnam Ltd.
Hochiminh office: 1st Floor, E.Town EW Building, 364 Cong Hoa Street, Ward 13, Tan Binh District, Ho Chi Minh City, Vietnam.
Tel : (84-8) 62971099 Fax : (84-8) 62971098 Email : consumergoods.vietnam@intertek.com
Hanoi office: 3rd Floor, Au Viet Building, No. 01 Le Duc Tho Street, Mai Dich Ward, Cau Giay District, Hanoi.
Tel : (84-4) 37337094 Fax : (84-4) 37337093 Website : www.intertek.com

TEST REPORT

NUMBER : VNMT16034374
DATE : 16-Aug-2016

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

1. Color Fastness To Washing

AATCC 61 - 2013. Test No. 2A, 45 Minutes Mechanical Wash At 120°F In 0.15% AATCC WOB 1993 Detergent Solution With 50 Steel Balls

Color Change	4.0
Self Staining	4.5
Color Staining	
Acetate	4.5
Cotton	4.5
Nylon	4.5
Polyester	4.5
Acrylic	4.5
Wool	4.5

2. Color Fastness To Water

AATCC 107 - 2013.

Color Change	4.5
Color Staining	
Acetate	4.5
Cotton	4.5
Nylon	4.5
Polyester	4.5
Acrylic	4.5
Wool	4.5

3. Color Fastness To Crocking

AATCC 8 - 2013.

Dry	4.5
Wet	4.5

4. Color Fastness To Light

AATCC 16.3 - 2012, Xenon Arc Lamp, Water Cooled

After 20 AFU	4.5

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)

Intertek Vietnam Ltd.
Hochiminh office: 1st Floor, E.Town EW Building, 364 Cong Hoa Street, Ward 13, Tan Binh District, Ho Chi Minh City, Vietnam.
Tel : (84-8) 62971099 Fax : (84-8) 62971098 Email : consumergoods.vietnam@intertek.com
Hanoi office: 3rd Floor, Au Viet Building, No. 01 Le Duc Tho Street, Mai Dich Ward, Cau Giay District, Hanoi.
Tel : (84-4) 37337094 Fax : (84-4) 37337093 Website : www.intertek.com

TEST REPORT

NUMBER : VNMT16034374
DATE : 16-Aug-2016

5. Seam Slippage/Strength

ASTM D1683 - 2011a

S.O. @ 1/4 Inch

// To Warp	18.9 lbs
// To Weft	*

REMARK:
* = The Seam Opening Was Less Than 1/4 Inch Though The Ultimate Seam Strength Was Found As Stated

END OF THE TEST REPORT

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at http://www.intertek.com/terms.

Intertek Vietnam Ltd.
Hochiminh office: 1st Floor, E.Town EW Building, 364 Cong Hoa Street, Ward 13, Tan Binh District, Ho Chi Minh City, Vietnam.
Tel : (84-8) 62971099 Fax : (84-8) 62971098 Email : consumergoods.vietnam@intertek.com
Hanoi office: 3rd Floor, Au Viet Building, No. 01 Le Duc Tho Street, Mai Dich Ward, Cau Giay District, Hanoi.
Tel : (84-4) 37337094 Fax : (84-4) 37337093 Website : www.intertek.com